




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : G02B 6/16, 6/124, 6/34	A1	(11) International Publication Number: WO 99/22256 (43) International Publication Date: 6 May 1999 (06.05.99)
(21) International Application Number: PCT/GB98/03176 (22) International Filing Date: 23 October 1998 (23.10.98) (30) Priority Data: 9722550.2 24 October 1997 (24.10.97) GB (71) Applicant (for all designated States except US): PIRELLI CAVI E SISTEMI S.P.A. [IT/IT]; Viale Sarca, 222, I-20126 Milan (IT). (72) Inventors; and (75) Inventors/Applicants (for US only): LAMING, Richard, Ian [GB/GB]; 62 Craigmillar Park, Edinburgh EH16 5PU (GB). IBSEN, Morten [DK/GB]; 10 Summit Way, Southampton, Hampshire SO19 4ST (GB). (74) Agent: TURNER, James, Arthur; D. Young & Co., 21 New Fetter Lane, London EC4A 1DA (GB).	(81) Designated States: AU, BR, CA, CN, JP, KR, NZ, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>	

(54) Title: FABRICATION OF OPTICAL WAVEGUIDE GRATINGS



(57) Abstract

Optical grating fabrication apparatus comprises a phase mask (40) for dividing an incident light beam (30) into a plurality of diffracted beams; and a focusing arrangement (60) for receiving light from the phase mask and converging at least two non-zero-order diffracted beams together so as to generate an interference region between the converged beams so that a grating structure can be impressed on an optical waveguide (80) placed in the interference region; the phase mask and at least a part of the focusing structure being moveable with respect to one another so as to alter the angle of convergence of the converged beams.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon	KR	Republic of Korea	PL	Poland		
CN	China	KZ	Kazakstan	PT	Portugal		
CU	Cuba	LC	Saint Lucia	RO	Romania		
CZ	Czech Republic	LI	Liechtenstein	RU	Russian Federation		
DE	Germany	LK	Sri Lanka	SD	Sudan		
DK	Denmark	LR	Liberia	SE	Sweden		
EE	Estonia			SG	Singapore		

FABRICATION OF OPTICAL WAVEGUIDE GRATINGS

This invention relates to methods and apparatus for fabricating optical waveguide gratings.

5 Optical waveguide gratings, such as optical fibre gratings, can be formed by exposing the core of an optical fibre to an interference pattern defining the period of the grating. The first experimental demonstration of fibre grating formation in the core of an optical fibre was by launching laser light along an optical fibre from an Argon-ion laser operating at 514 nm, so that a grating was formed over the entire
10 length of the fibre.

More recent techniques have used interference patterns incident on the side of the fibre to impress a grating structure on photosensitive regions within the fibre core and/or cladding.

15 The methods used to generate such an interference pattern have included prism-interferometers [see publication reference "Broer" cited below], diffraction grating / phase-masks [Anderson] and combined phase-mask and prism-interferometers [Armitage]. A further development is described in GB-A-2 272 075, where a phase mask is imaged onto the fibre core using a lens.

20 However, an established problem is that of tuning the pitch of the grating in the fabrication process - for example, to generate a long (several centimetres or more) chirped grating where the pitch varies along the length of the grating.

25 This is a very difficult task with an multi-beam interferometer, because the coherence length of the writing laser beam makes careful matching of the different optical paths critical to maintaining a good visibility of the generated interference pattern.

30 Tuning of the grating pitch from uniform phase masks have been reported before from both a phase mask magnification technique [Prohaska] and a tuning scheme based on a beam diameter dependant maximum tuning [Cole and GB9509874.5]. In both cases the maximum tuning possible is ~ (about) 10 nm (nanometres) with the latter system being the more flexible.

The present invention provides optical grating fabrication apparatus comprising:

a phase mask for dividing an incident light beam into a plurality of diffracted beams; and

a focusing arrangement for receiving light from the phase mask and converging at least two non-zero-order diffracted beams together so as to generate an interference region between the converged beams so that a grating structure can be
5 impressed on an optical waveguide placed in the interference region;

the phase mask and at least a part of the focusing arrangement being moveable with respect to one another so as to alter the angle of convergence of the converged beams.

10 In the invention, a phase mask is imaged onto the waveguide using a lens. However, rather than the usual step of fixing the relative positions of the phase mask and lens to a separation equal to the focal length of the lens (which would normally be expected for maximum mechanical stability of the system), the counter-intuitive step is taken of altering the separation of the phase mask and lens to alter the angle
15 of convergence of the converged beams. The skilled man will immediately then understand that this in turn alters the fringe pitch incident on the waveguide.

Prototype embodiments of the invention can demonstrate a tuning range of 27nm, i.e. about three times the best tuning range so far reported.

20 The advantages of the invention compared with other techniques used to write fibre Bragg gratings and in particular when used together with techniques where the fibre is moved in the interference pattern behind the either chirped or uniform phase-mask, e.g the 'Step and repeat' technique, by GB9617688.8, are that it provides no contact or close contact between the fibre and phase mask thereby avoiding the static electricity that builds up between moving glass surfaces.

25 By using a lens, the writing beam power can be focused more precisely onto the optical waveguide core of the grating host rather than through the side of e.g the optical fibre.

30 It has been known for two years before the priority date of this application [Ouellette] that the production of long phase-masks (>5 cm) is not possible with continuous techniques, and so step-write e-beam techniques must be employed. The repeat precision between concatenated sections, however, is not good enough to ensure a separation on the phase-mask period thereby introducing periodic 'stich-

errors' along the length of the phase-mask. Imperfect overlap regions will cause phase-shifts that will reduce the quality of the gratings written from such a phase-mask. Even scanning along non-stitched phase-mask will limit the grating quality to the uniformity in the groove depth pattern of the phase-mask. A variation in the groove depth of the phase-mask will cause a power fluctuation in the zeroth-order hence power fluctuations in the interfering -1st and 1st orders of the phase-mask thereby leading to an increased background (dc) level in the grating and a reduction in the visibility of interference pattern. All these factors have tended to reduce the quality of the gratings produced. In contrast, the invention can avoid or alleviate this phase-mask grating quality degradation simply because the writing beam position on the phase-mask can be kept constant.

Although the invention can be embodied as a 'free-space' interferometer (sometimes perceived as a disadvantage), the invention can in fact be embodied using only a single lens to catch and recombine the interfering beams. Furthermore, the tuning scheme is advantageously simplified because it only includes a relative movement of the lens with respect to the phase mask. If this movement is made along the direction of the writing beam, the coherence between the two interfering beams is not affected.

The invention also provides an optical grating fabrication method comprising the steps of: directing a light beam onto a phase mask to divide the light beam into a plurality of diffracted beams; converging at least two non-zero-order diffracted beams together using a focusing arrangement so as to generate an interference region between the converged beams so that a grating structure can be impressed on an optical waveguide placed in the interference region; and providing relative movement between the phase mask and at least a part of the focusing arrangement so as to alter the angle of convergence of the converged beams.

The invention will now be described by way of example only with reference to the accompanying drawings in which:

Figure 1 is a schematic diagram of grating fabrication apparatus according to an embodiment of the invention;

Figure 2 is a graph showing theoretical tuning curves for relative lens movement;

Figure 3a illustrates an empirical tuning curve for a lens with $f = 17.7$ mm, with a fixed lens position and a moving phase-mask position;

Figure 3b illustrates an empirical tuning curve for a lens with $f = 17.7$ mm, with a fixed phase-mask position and a moving lens position;

5 Figures 4a and 4b illustrate empirical reflection and time delay characteristics of a 85 cm long linearly chirped fibre grating written with the interferometer of Figure 1.

Referring now to Figure 1, a laser source (e.g. a UV laser source) 10 and a collimating lens 20 generate a collimated beam of UV light 30. The beam is incident on a phase mask 40, giving rise to so-called 0th-order, -1st order and 1st order diffracted beams (and possibly other higher order beams which are not relevant to the present explanation). The 0th order beam propagates in the same direction as the incident beam, whereas the -1st and 1st order beams are angularly deviated with respect to the incident beam, as illustrated.

15 An opaque block 50 is placed in the path of the 0th-order beam, so that only the -1st and 1st order beams are incident on an anti reflection coated biconvex spherical lens 60.

20 The -1st and 1st order beams incident on the lens 60 are brought to a focus in a region 70 overlapping the core (or other region in which a grating is to be impressed) of an optical fibre waveguide 80. An interference pattern is formed between the two beams, and a grating structure is written at the pitch of the interference fringes.

25 Apart from any translation stage (not shown) which may be used to scan the writing beam along the fibre (or vice versa - see GB9617688.8), the phase mask 40 and/or the lens 60 are mounted on a translation stage 90 (shown in schematic dotted line for clarity of the diagram) which, under the control of a control circuit 100, is arranged to alter the relative separation of the phase mask 40 and the lens 60. The effect of such a separation, and some experimental results obtained using this technique, will be described further below.

30 For the following discussions, the distance from the interference point on the phase-mask P_1 to the lens is denoted by d_1 and the distance from the lens to the image point P_2 is denoted by d_2 . The period of the phase-mask is called λ_{pm} and the focal

length of the lens f . From the literature is known that the angle between the diffracted orders through the phase-mask is given by

$$\theta_{pm} = \sin^{-1}\left(\frac{\lambda_i}{\lambda_{pm}}\right) \quad (1)$$

with λ_i being the wavelength of the light incident perpendicular on the phase-mask. The angle between the interfering -1 and 1 order is therefore $2\theta_{pm}$. The period of the interference is

$$\Lambda = \frac{\lambda_i}{2 \sin(\theta_{pm})} \quad (2)$$

The relation between the focal length f , d_1 and d_2 is according to the *imaging equation* given by

$$\frac{1}{f} = \frac{1}{d_1} + \frac{1}{d_2} \quad (3)$$

and therefore in the case of 1:1 imaging of P_1 in P_2 , $d_1 = d_2 = 2f$.

To relate exemplary numbers to the equations presented above a phase-mask period of 1060 nm and UV-light of wavelength 244 nm is used. From (1) this gives a separation angle of 13.31° between the diffracted orders and therefore 26.62° between the -1 and 1 order. According to (2) this gives a period of 530 nm of the interference pattern. If a standard lens diameter D of 25.4 mm (1 inch) is chosen the clear diameter D_{cl} of a lens is typically the centre 85% of the diameter. Hence D_{cl} is 21.6 mm. The maximum distance from the phase-mask to the lens is d_{max} :

$$\tan(\theta_{pm}) = \frac{\frac{1}{2} \cdot D_{cl}}{d_{max}} \quad (4)$$

and therefore

$$\begin{aligned} d_{\max} &= \frac{D_{cl}}{2 \tan(\theta_{pm})} \quad (5) \\ &= \underline{45.6 \text{ mm}} \end{aligned}$$

According to (3) the maximum focal length of a 1 inch lens then has $f_{\max} = 22.8$ mm.

5 Tuning of the period of the interfering beams and hence tuning of the Bragg wavelength can be achieved by varying the distance d_1 . According to the imaging equation (3) the relation of d_2 for fixed f and varying d_1 is

$$d_2(d_1) = \frac{f}{1 - \frac{f}{d_1}}, \quad d_1 \in [f; d_{\max}] \quad (6)$$

If the beam is assumed to exit the lens at the same distance from the centre-axis of the lens as it enters it, as is the case of the thin-lens approximation, the relation between θ_{pm} and θ_{im} , see Figure 1, becomes

$$\tan(\theta_{im}) \cdot d_2 = \tan(\theta_{pm}) \cdot d_1 \Rightarrow \underline{\theta_{im} = \tan^{-1}\left(\frac{d_1}{d_2} \tan(\theta_{pm})\right)} \quad (7)$$

10 Now an expression for the angle between the interfering beams in the imaging plane as function of d_1 has been obtained, an expression for the Bragg wavelength tuning as function of detuning from the 1:1 imaging case can be obtained. This expression becomes

$$\Delta \lambda_B = n_{ave} \cdot \lambda_i \cdot \left(\frac{1}{\sin(\theta_{im})} - \frac{1}{\sin(\theta_{pm})} \right) \quad (8)$$

where n_{ave} is the average refractive index in the grating.

Figure 2 shows a graph of equation (8) for different values of f with $n_{ave}=1.46$. From Figure 2 is seen that employing a shorter focal length lens gives a higher wavelength shift per unit length change and hence higher precision on the tuning of d_1 is required.

The maximum detuning to shorter wavelengths is obtained with $d_1=d_{max}$ giving the maximum angle between the interfering beams in the imaging plane. In principle any Bragg wavelength above the wavelength defined by the phase-mask can be achieved by tuning d_1 towards f .

One advantage of this method to tune the pitch of a phase-mask is that the width of the interfering beams is no more limited to the approx. 30 μm diameter beam in front of the phase-mask. This diameter is required in order to expose the fibre core with the interfering UV coming from the splitting angle of the orders from the phase-mask, see (1).

This method enables the interfering beams to be focused on the fibre core instead of on the side of the fibre and therefore have higher fluence in the region of interest. Another point is that very wide-band chirped gratings can be fabricated by scanning the lens during writing. Furthermore this technique optimises the writing of superstructure gratings that often requires grating subsection lengths down to $\sim 20 \mu\text{m}$.

Ideally, the translation stage 90 that controls the position of the lens with respect to the phase-mask needs a precision of $\sim 1 \mu\text{m}$ and should have a maximum travel of a few hundred microns in order to make use of the full potential of the method. However, less precise stages and/or stages with lesser travels can of course be used.

A collimated beam on the phase-mask is preferred in order to avoid any distortion coming from a diverging beam. The latter point can be addressed by providing the collimating lens 20 or a collimating telescope in its place before the phase-mask.

Some of the issues discussed above are summarised in the table I below.

TABLE I

Comments \forall	10 mm	15 mm	18 mm	20 mm	22.6 mm
Minimum λ_p	553.1 nm	819.7 nm	1044.8 nm	1229.3 nm	1547.6 nm
Device length	~ 6 cm	~ 7 cm	~ 8 cm	~ 9 cm	~ 10 cm
Tuning slope	1.4 nm / 10 μ m	1 nm / 10 μ m	0.83 nm / 10 μ m	0.75 nm / 10 μ m	0.7 nm / 10 μ m

The numbers in table I are based on

$$\lambda_{pm}=1060 \text{ nm}$$

$$\lambda_f=244 \text{ nm}$$

$$n_{ave}=1.46$$

Lens diameter; 25.4 mm

Figures 3a, 3b, 4a and 4b illustrate empirical results obtained with a prototype device according to Figure 1.

Figures 3a and 3b illustrate two tuning curves obtained for a lens with a focal length $f=17.7$ mm and $\lambda_{pm}=1057.1$ nm. Figure 3a shows a tuning range from 1535.5 nm to 1550 nm with a slope of 0.94nm/10 μ m obtained by moving the phase-mask and keeping the lens in a fixed position. Figure 3b shows a tuning range from 1522 nm to 1549 nm with a slope of 0.92 nm/10 μ m obtained by moving the lens and for fixed phase-mask position.

Figures 4a and 4b illustrate empirical reflection and time delay characteristics of a linearly chirped fibre grating written with the interferometer of Figure 1. The grating is 85 cm long has a 3 nm bandwidth and is written using 100 mW of CW UV-light from a frequency doubled Ar-ion laser. The grating is written in a D₂-loaded high NA (0.2) fibre.

The advantage of using a bi-convex lens to catch and recombine the diffracted orders from the phase mask is that it is known as the 'best form' for 1:1 imaging.

This because it does not introduce any aberrations. Furthermore the embodiment is simple and robust it employs only one lens element within the interferometer. Moreover, by blocking the transmitted 0th order beam from the phase mask a better visibility is obtained in the interference pattern between the interfering -1 and 1 orders.

5 Certain precautions can be taken into account in order to further improve the performance of the interferometer of Figure 1. One of these is that the best results are expected to be obtained when the interference point in the imaging plane is composed of plane waves. This is obtained by focusing the collimated writing beam on to the phase mask with a lens that has exactly *twice* the focal length to that of the
10 interferometer lens itself.

The apparatus of Figure 1 has been used to produce an 85 cm long chirped fibre grating written with an interferometer with a 1 inch diameter lens to show the practicality of such a device in terms of the compactness (a prototype device length of just ~ 7 cm), but the skilled man will of course appreciate that interferometers with
15 bigger lenses might be more practical for specific purposes, where the reduced tolerance on the tuning of the Bragg wavelength from bigger lenses might be perceived as an advantage.

The apparatus, as mentioned above, lends itself to use with a system such as that described in GB9617688.8, namely a technique involving fabricating an optical
20 waveguide grating having a plurality of grating lines of refractive index variation, the and comprising the steps of:

- (i) repeatedly exposing a spatially periodic writing light pattern onto a photosensitive optical waveguide; and
- (ii) moving the writing light pattern and/or the waveguide between successive
25 exposures of the writing light pattern, so that each of at least a majority of the grating lines is generated by at least two exposures to different respective regions of the writing light pattern.

In such a technique, the apparatus and methods described earlier can easily be used to provide a writing light beam of varying grating pitch. The movement between
30 the writing beams and the waveguide can be achieved by one or more translation stages or possibly by tilting the lens 60.

PUBLICATION REFERENCES

- 5 [Meltz] MELTZ, G., MOREY, W. W. and GLENN, W. H.: 'Formation of Bragg gratings in optical fibers by a transverse holographic method', *Optics Lett.*, **14**, (15), pp. 823-825, 1989.
- 10 [Anderson] ANDERSON, D. Z., MIZRAHI, V., ERDOGAN, T. and WHITE, A. E.: 'Production of in-fibre gratings using a diffractive optical element', *Electron. Lett.*, **29**, (6), pp. 566-568, 1993.
- 15 [Hill] HILL, K. O., MALO, B., BILODEAU, F., JOHNSON, D. C. and ALBERT, J.: 'Bragg gratings fabricated in monomode photosensitive optical fiber by UV exposure through a phase mask', *Appl. Phys. Lett.*, **62**, (10), pp. 1035-1037, 1993.
- 20 [Malo] MALO, B., HILL, K. O., BILODEAU, F., JOHNSON, D. C. and ALBERT, J.: 'Point-by-point fabrication of micro-Bragg gratings in photosensitive fibre using single excimer pulse refractive index modification techniques', *Electron. Lett.*, **29**, (18), pp. 1668-1669, 1993.
- 25 [Broer] BROER, M. M., CONE, R. L. and SIMPSON, J. R.: 'Ultraviolet-induced distributed-feedback gratings in Ce^{3+} -doped silica optical fibers', *Optics Lett.*, **16**, (18), pp. 1391-1393, 1991.
- [Armitage] ARMITAGE, J. R.: 'Fibre Bragg reflectors written at 262 nm using a frequency quadrupled diode-pumped Nd^{3+} : YLF laser', *Electron. Lett.*, **29**, (13), pp. 1181-1183, 1993.
- 30 [Prohaska] PROHASKA, J. D., SNITZER, E., RISHTON, S. and BOEGLI, V.: 'Magnification of mask fabricated fibre Bragg gratings', *Electron. Lett.*, **29**, (18), pp. 1614-1615, 1993.

[Cole] COLE, M. J., LOH, W. H., LAMING, R. I., ZERVAS, M. N. and BARCELOS, S.: 'Moving fibre/phase mask scanning beam technique for enhanced flexibility in producing fibre gratings with a uniform phase mask', *Electron. Lett.*, **31**, (12), pp. 1488-1489, 1995.

5

[Ouellette] OUELLETTE, F., KRUG, P. A. and PASMAN, R.: 'Characterization of long phase masks for writing fiber Bragg gratings', *Optical Fiber Technol.*, **2**, (3), pp. 281-284, 1996.

CLAIMS

1. Optical grating fabrication apparatus comprising:

5 a phase mask for dividing an incident light beam into a plurality of diffracted beams; and

a focusing arrangement for receiving light from the phase mask and converging at least two non-zero-order diffracted beams together so as to generate an interference region between the converged beams so that a grating structure can be impressed on an optical waveguide placed in the interference region;

10 the phase mask and at least a part of the focusing arrangement being moveable with respect to one another so as to alter the angle of convergence of the converged beams.

15 2. Apparatus according to claim 1, in which the focusing arrangement consists of a single lens.

3. Apparatus according to claim 2, in which the lens is a biconvex spherical lens.

20 4. Apparatus according to any one of claims 1 to 3, comprising a collimating arrangement for substantially collimating the beam incident on the phase mask.

25 5. Apparatus according to claim 4 as dependent on claim 2 or claim 3, in which the collimating arrangement comprises a lens that has twice the focal length as that of the firstmentioned lens.

30 6. Apparatus according to any one of the preceding claims, comprising a translation apparatus for providing relative translation of the grating fabrication apparatus and an optical waveguide in which a grating is to be fabricated, so that the interference region can be incident on different portions of the optical waveguide.

7. Apparatus according to any one of the preceding claims, in which the waveguide is an optical fibre waveguide.

8. Apparatus according to any one of the preceding claims, the apparatus comprising means for repeatedly exposing the interference region onto the waveguide; and


5 means for moving the interference region and/or the waveguide between successive exposures of the writing light pattern, so that each of at least a majority of the grating lines of the waveguide grating is generated by at least two exposures to the interference region.

9. An optical grating fabrication method comprising the steps of:

10 directing a light beam onto a phase mask to divide the light beam into a plurality of diffracted beams;

converging at least two non-zero-order diffracted beams together using a focusing arrangement so as to generate an interference region between the converged beams so that a grating structure can be impressed on an optical waveguide placed in
15 the interference region; and

providing relative movement between the phase mask and at least a part of the focusing arrangement so as to alter the angle of convergence of the converged beams.






FIG. 2

3 / 6




FIG.3a

4 / 6




FIG.3b

5 / 6




FIG. 4a

6 / 6




FIG.4b

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 98/03176

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 G02B6/16 G02B6/124 G02B6/34

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 G02B G03F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 782 018 A (ALSTHOM CGE ALCATEL) 2 July 1997 see the whole document ---	1,2,6-9
A	US 5 655 040 A (SANSONETTI PIERRE ET AL) 5 August 1997 see the whole document ---	1,4,7-9
A	EP 0 684 491 A (NORTHERN TELECOM LTD) 29 November 1995 see column 1, line 1 - line 58 see column 2, line 1 - line 26 see figure 6 ---	1,7,9
A	US 5 482 801 A (SMITH ADLAI H ET AL) 9 January 1996 see the whole document ---	1,2,4,9
-/--		

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

13 January 1999

Date of mailing of the international search report

21/01/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Mathyssek, K

INTERNATIONAL SEARCH REPORT

International Application No
PCT/GB 98/03176

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>US 5 367 588 A (BILODEAU FRANCOIS C ET AL) 22 November 1994 cited in the application see column 1, line 57 - line 68 see column 2, line 1 - line 48 see column 6, line 31 - line 51 see figure 5</p>	1,2,7,9
A	<p>ARMITAGE J R: "FIBRE BRAGG REFLECTORS WRITTEN AT 262 NM USING A FREQUENCY QUADRUPLD DIODE-PUMPED ND3+: YLF LASER" ELECTRONICS LETTERS, vol. 29, no. 13, 24 June 1993, pages 1181-1183, XP000378395 cited in the application</p>	1,9

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 98/03176

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0782018	A	02-07-1997	FR 2742881 A	27-06-1997
			AU 7548696 A	03-07-1997
			CA 2194005 A	27-06-1997
			JP 9189819 A	22-07-1997
			US 5768454 A	16-06-1998
US 5655040	A	05-08-1997	FR 2728356 A	21-06-1996
			AU 4037995 A	20-06-1996
			CA 2165266 A	16-06-1996
			EP 0721118 A	10-07-1996
EP 0684491	A	29-11-1995	GB 2289771 A	29-11-1995
			US 5619603 A	08-04-1997
US 5482801	A	09-01-1996	WO 9530932 A	16-11-1995
			US 5328785 A	12-07-1994
			AU 6828094 A	29-11-1995
			JP 9512749 T	22-12-1994
US 5367588	A	22-11-1994	CA 2087511 A	30-04-1994
			DE 4337103 A	05-05-1994
			FR 2697642 A	06-05-1994
			GB 2272075 A,B	04-05-1994
			JP 7140311 A	02-06-1995